



# ASACHEM (M) SDN. BHD. (Co. No.: 1992-0101-5904)

3, First Floor, Jalan Seksyen 3/8, Kajang Utama, 43000 Kajang, Selangor, Malaysia.

Tel : 603 - 8734 5998

Website: [www.asachem.com](http://www.asachem.com)

Email : [info@asachem.com](mailto:info@asachem.com)

## Silica Sand (Fine)

Type of Sand	CUMULITIVE RETAINED					
	MM	0.25	0.212	0.18	0.15	0.125
	MICRONS	250	212	180	150	125
	MESH - US	60	70	80	100	120
	MESH - BSS	60	72	85	100	120
<b>Silica Sand Fine</b>	10	62	74	84	100	

### ANALYSIS REPORT

TEST ITEM		UNIT	RESULT
SILICA	SiO <sub>2</sub>	%	98.8
IRON	Fe <sub>2</sub> O <sub>3</sub>	%	0.095
ALUMINIUM	Al <sub>2</sub> O <sub>3</sub>	%	0.241
MAGNESIUM	Mgo	%	0.014
TITANIUM	TiO <sub>2</sub>	%	0.004
SPECIFIC GRAVITY		-	2.63
LOSS OF IGNITION		%	0.38

### Disclaimer

The information given in this data sheet is based on the present state of our knowledge and any conclusion and recommendation are without liability on our part. Buyers and users should make their own assessment of our products under their own conditions and for their own requirements.