



# ASACHEM (M) SDN. BHD. (Co. No.: 1992-0101-5904)

3, First Floor, Jalan Seksyen 3/8, Kajang Utama, 43000 Kajang, Selangor, Malaysia.

Tel : 603 - 8734 5998

Website: [www.asachem.com](http://www.asachem.com)

Email : [info@asachem.com](mailto:info@asachem.com)

## Silica Sand (Medium)

Type of Sand	CUMULITIVE RETAINED					
	MM	0.6	0.425	0.3	0.25	0.212
	MICRONS	600	425	300	250	212
	MESH - US	30	40	50	60	70
	MESH - BSS	25	36	52	60	72
<b>Silica Sand Coarse</b>	<b>10</b>	<b>38</b>	<b>82</b>	<b>88</b>	<b>100</b>	

### ANALYSIS REPORT

TEST ITEM		UNIT	RESULT
SILICA	SiO <sub>2</sub>	%	99.2
IRON	Fe <sub>2</sub> O <sub>3</sub>	%	0.082
ALUMINIUM	Al <sub>2</sub> O <sub>3</sub>	%	0.141
MAGNESIUM	MgO	%	<0.01
TITANIUM	TiO <sub>2</sub>	%	<0.001
SPECIFIC GRAVITY		-	2.63
LOSS OF IGNITION		%	0.27

### Disclaimer

The information given in this data sheet is based on the present state of our knowledge and any conclusion and recommendation are without liability on our part. Buyers and users should make their own assessment of our products under their own conditions and for their own requirements.