



# ASACHEM (M) SDN. BHD. (Co. No.: 1992-0101-5904)

3, First Floor, Jalan Seksyen 3/8, Kajang Utama, 43000 Kajang, Selangor, Malaysia.

Tel : 603 - 8734 5998

Website: [www.asachem.com](http://www.asachem.com)

Email : [info@asachem.com](mailto:info@asachem.com)

## **Silica Sand (COARSE)**

Type of Sand	CUMULITIVE RETAINED			
	MM	2.00	1	0.85
	MICRONS	-	-	850
	MESH - US	10	16	20
	MESH - BSS	8	16	18
<b>Silica Sand Coarse</b>	<b>16</b>	<b>94</b>	<b>100</b>	

### ANALYSIS REPORT

TEST ITEM		UNIT	RESULT
SILICA	SiO <sub>2</sub>	%	98.7
IRON	Fe <sub>2</sub> O <sub>3</sub>	%	0.019
ALUMINIUM	Al <sub>2</sub> O <sub>3</sub>	%	0.093
MAGNESIUM	MgO	%	<0.01
TITANIUM	TiO <sub>2</sub>	%	<0.001
SPECIFIC GRAVITY		-	2.65
LOSS OF IGNITION		%	0.22

### **Disclaimer**

The information given in this data sheet is based on the present state of our knowledge and any conclusion and recommendation are without liability on our part. Buyers and users should make their own assessment of our products under their own conditions and for their own requirements.